

Data sheet article Q-10-05-01-STIC

Technical data and application safety

Webcraft GmbH Industriepark 206 78244 Gottmadingen, Germany

Phone: +49 7731 939 839 1

www.supermagnete.hu support@supermagnete.hu

1. Technical information

Neodymium supermagnet - Block magnet self-adhesive 10 x 5 x 1 mm, holds approx. 500 g

EAN7640155435994MaterialNdFeBShapeBlockSize10 x 5 x 1 mmSide 110 mmSide 25 mmSide 31 mmPole faces10 x 5 mmTolerance+/- 0,1 mmDirection of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °C	Article ID	O-10-05-01-STIC
MaterialNdFeBMaterialNdFeBShapeBlockSize $10 \times 5 \times 1 \text{ mm}$ Side 110 mmSide 25 mmSide 31 mmPole faces $10 \times 5 \text{ mm}$ Tolerance $+/- 0,1 \text{ mm}$ Direction of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc>12 kOe, ≥955 kA/m		
NationalBlockShapeBlockSize $10 \times 5 \times 1 \text{ mm}$ Side 1 10 mm Side 2 5 mm Side 3 1 mm Pole faces $10 \times 5 \text{ mm}$ Tolerance $+/-0,1 \text{ mm}$ Direction of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature 80° C (possibly lower) *ColourSilver-colouredAdhesive $3M$, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature $310 ^{\circ}$ CResidual magnetism Br $11700-12100 \text{ G}, 1.17-1.21 \text{ T}$ Coercive field strength bHc $212 \text{ kOe}, \ge 955 \text{ kA/m}$		
Size10 x 5 x 1 mmSide 110 mmSide 25 mmSide 31 mmPole faces10 x 5 mmTolerance+/- 0,1 mmDirection of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc≥12 kOe, ≥955 kA/m	material	
Side 110 mmSide 25 mmSide 31 mmPole faces 10×5 mmTolerance $+/-0,1$ mmDirection of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc $>12 \text{ KOe}, \ge 955 \text{ KA/m}$		
Side 25 mmSide 31 mmPole faces10 x 5 mmTolerance $+/- 0,1$ mmDirection of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc>12 kOe, ≥955 kA/m		
Side 31 mmPole faces 10×5 mmTolerance $+/-0,1$ mmDirection of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature 80° C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc 212 kOe, ≥ 955 kA/m		
Pole faces $10 \times 5 \text{ mm}$ Tolerance $+/-0,1 \text{ mm}$ Direction of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature 80° C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature $310 ^{\circ}$ CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc $>12 kOe, \ge 955 kA/m$		•
Tolerance+/- 0,1 mmDirection of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature 80° C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc ≥ 12 kOe, ≥ 955 kA/m		
Direction of magnetisationMagnetised heightwiseCoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc212 kOe, ≥955 kA/m		
CoatingNickel-plated (Ni-Cu-Ni)Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature 80° C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc>12 kOe, ≥955 kA/m	Tolerance	,
Manufacturing methodsinteredMagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc≥12 kOe, ≥955 kA/m	Direction of magnetisation	Magnetised heightwise
MagnetisationN35Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc≥12 kOe, ≥955 kA/m	Coating	Nickel-plated (Ni-Cu-Ni)
Strengthapprox. 500 g (approx. 4,9 N)Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc≥12 kOe, ≥955 kA/m		sintered
Displacement forceapprox. 100 g (approx. 0,981 N)Max. working temperature80°C (possibly lower) *ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc≥12 kOe, ≥955 kA/m	Magnetisation	N35
Max. working temperature80°C (possibly lower)*ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc≥12 kOe, ≥955 kA/m	Strength	approx. 500 g (approx. 4,9 N)
ColourSilver-colouredAdhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc≥12 kOe, ≥955 kA/m	Displacement force	approx. 100 g (approx. 0,981 N)
Adhesive3M, No. 467MPShelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc ≥ 12 kOe, ≥ 955 kA/m	Max. working temperature	80°C (possibly lower) *
Shelf life adhesive12 months (approx.)DesignSelf-adhesive (film)Weight $0,3800 \text{ g}$ Curie temperature $310 ^{\circ}\text{C}$ Residual magnetism Br $11700-12100 \text{ G}, 1.17-1.21 \text{ T}$ Coercive field strength bHc $10.8-11.5 \text{ kOe}, 860-915 \text{ kA/m}$ Coercive field strength iHc $\geq 12 \text{ kOe}, \geq 955 \text{ kA/m}$	Colour	Silver-coloured
DesignSelf-adhesive (film)Weight0,3800 gCurie temperature310 °CResidual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc≥12 kOe, ≥955 kA/m	Adhesive	3M, No. 467MP
Weight0,3800 gCurie temperature $310 ^{\circ}C$ Residual magnetism Br $11700-12100 G, 1.17-1.21 T$ Coercive field strength bHc $10.8-11.5 kOe, 860-915 kA/m$ Coercive field strength iHc $\geq 12 kOe, \geq 955 kA/m$	Shelf life adhesive	12 months (approx.)
Curie temperature $310 ^{\circ}\text{C}$ Residual magnetism Br $11700-12100 \text{G}, 1.17-1.21 \text{T}$ Coercive field strength bHc $10.8-11.5 \text{kOe}, 860-915 \text{kA/m}$ Coercive field strength iHc $\geq 12 \text{kOe}, \geq 955 \text{kA/m}$	Design	Self-adhesive (film)
Residual magnetism Br11700-12100 G, 1.17-1.21 TCoercive field strength bHc10.8-11.5 kOe, 860-915 kA/mCoercive field strength iHc≥12 kOe, ≥955 kA/m	Weight	0,3800 g
Coercive field strength bHc 10.8-11.5 kOe, 860-915 kA/m Coercive field strength iHc ≥12 kOe, ≥955 kA/m	Curie temperature	310 °C
Coercive field strength bHc 10.8-11.5 kOe, 860-915 kA/m Coercive field strength iHc ≥12 kOe, ≥955 kA/m	Residual magnetism Br	11700-12100 G, 1.17-1.21 T
Coercive field strength iHc ≥12 kOe, ≥955 kA/m	J	10.8-11.5 kOe, 860-915 kA/m



* Based on the dimensions it is possible that this magnet has a reduced temperature resistance. Please review our FAQ: <u>https://www.supermagnete.hu/faq/What-temperatures-can-magnets-withstand#pu424</u>

ROHS Product compliant with the latest European RoHS directive.

Product compliant with the latest European REACH regulation.

REACH

2. Safety tips

Danger	Swallowing
	Children could swallow small magnets. If several magnets are swallowed, they could get stuck in the intestine and cause perilous complications.
9 0-14	Magnets are not toys! Make sure that children don't play with magnets.
Warning	Pacemaker
	 Magnets could affect the functioning of pacemakers and implanted heart defibrillators. A pacemaker could switch into test mode and cause illness. A heart defibrillator may stop working.
	 If you wear these devices keep sufficient distance to magnets: www.supermagnete.hu/faq/distance Warn others who wear these devices from getting too close to magnets.
Warning	Metal splinters
	Neodymium magnets are brittle. Colliding magnets could crack. Sharp splinters could be catapulted away for several meters and injure your eyes.
ć	 Avoid the collision of magnets. Wear safety glasses when handling larger magnets. Make sure that nearby people are also protected or keep their distance.

3. Handling and storing

Caution	Magnetic field
	Magnets produce a far-reaching, strong magnetic field. They could damage TVs and laptops, computer hard drives, credit and ATM cards, data storage media, mechanical watches, hearing aids and speakers.
	 Keep magnets away from devices and objects that could be damaged by strong magnetic fields. Please refer to our table of recommended distances: www.supermagnete.hu/faq/distance

Caution	Combustibility
	When machining magnets, the drilling dust could easily ignite.
	Stay away from machining magnets or use appropriate tools and sufficient cooling water.

Caution	Nickel allergy
	 Many of our magnets contain nickel, also those without nickel coating. Some people have an allergic reaction when they come into contact with nickel. Nickel allergies could develop from perpetual contact with nickel-plated objects.
	 Avoid perpetual skin contact with magnets. Avoid contact with magnets if you already have a nickel allergy.
Notice	Influence on people
	According to the current level of knowledge, magnetic fields of permanent magnets do not have a measurable positive or negative influence on people. It is unlikely that permanent magnets constitute a health risk, but it
	cannot be ruled out entirely.

Notice	Splintering of coating
	Most of our neodymium magnets have a thin nickel-copper-nickel coating to protect them from erosion. This coating could splinter or crack due to collision or large pressure. This makes them vulnerable to environmental influences like moisture and they could oxidise.
	 Separate big magnets, especially spheres, with a piece of cardboard. Avoid collisions of magnets as well as repeated mechanical exposure (e.g. blows, bashes).
Notico	Ovidation correction rust

Notice	Oxidation, corrosion, rust
0	Untreated neodymium magnets oxidise quickly and disintegrate. Most of our magnets have a nickel-copper-nickel coating to protect them from corrosion. This coating provides some protection against corrosion, but it is not robust enough for continuous outdoor use.
	 Use magnets only in the dry indoors or protect them against environmental influences. Avoid damages to the coating.

Notice	Temperature resistance
	Depending on the magnet type, neodymium magnets have a maximum working temperature of 80 to 200 °C. Very thin neodymium magnets and magnets with N52 magnetisation have a maximum working temperature of 65 °C. Most neodymium magnets lose part of their adhesive force permanently at a temperature of 80°C.
	 Don't use magnets in places where they are exposed to extreme heat. If you use an adhesive, don't harden it with hot air. Please note our overview of temperature resistance.
Notico	Machanical treatment

Notice	Mechanical treatment
	 Neodymium magnets are brittle, heat-sensitive and oxidise easily. When drilling or sawing a magnet with improper tools, the magnet may break. The emerging heat may demagnetise the magnet. The magnet will oxidise and disintegrate due to the damaged coating.
	Avoid machining magnets if you do not have the necessary machines and experience. Let us provide you with an offer for a custom-made order instead: www.supermagnete.hu/custom_form.php

4. Transportation tips

Caution	Airfreight
	Magnetic fields of improperly packaged magnets could influence airplane navigation devices. In the worst case it could lead to an accident.
	 Airfreight magnets only in packaging with sufficient magnetic shielding. Please refer to the respective regulations: www.supermagnete.hu/faq/airfreight
Caution Postage Magnetic fields of improperly packaged magnets could cause disturbances in sortin fragile goods in other packages.	Postage
	Magnetic fields of improperly packaged magnets could cause disturbances in sorting machines and damage fragile goods in other packages.

fragile goods in other packages.	5
 Please refer to our shipping tips: www.supermagnete.hu/faq/shipping Use a large box and place the magnet in the middle surrounded by lots of padding material. Arrange magnets in a package in a way that the magnetic fields neutralise each other. If necessary, use sheet iron to shield the magnetic field. There are stricter rules for airfreight: Refer to the warning notice "Airfreight". 	

5. Disposal tips

Small amounts of used neodymium magnets can be thrown out with the regular trash. Larger amounts of magnets need to be recycled as scrap metal.

6. Statutory provisions

Please note that the export of neodymium magnets to the US, Canada and Japan may be subject to patent restrictions. We recommend that you clarify the legal aspects before exporting to these countries.

TARIC-Code: 8505 1110 99 0

Origin: China

For more information about magnets please review **https://www.supermagnete.hu/faqs**.

Last update: 21/11/2024